



T (450) 978-3403

1 (888) 528-8518

F (450) 978-2542

3229 Nord Autoroute Laval (A-440) Ouest
Laval, QC H7P 5P2

www.duro-design.com

Technical Specifications for DuroDesign Cork Tile Flooring

Installation Method	Glue-down
Tile dimensions	12" x 12" or 12" x 24" x 8mm (5/16") thick
Density	500 kg/m ³ average
Thermal Insulation	Coefficient of Conductivity for densities of: 450 kg/2 = 0.958 kcal/m ² ho C 600 kg/2 = 0.1285 kcal/m ² ho C
Humidity Resistance	Under exposure to constant humidity and alternating exposure to humidity and heat, tiles neither swell nor come unglued
Compression & Recovery (ISO 9727)	With loading of 7 kg/cm ² , initial 10%, residual (after 1 hour) 1.5%; breaking tension on traction, not less than 2 kg/cm
Dimensional Tolerance	Length-width = -0.5, thickness = /0.2 squaring; deviation not greater than 0.2 mm (0.256")
Fire Rating (ASTM E648)	Class II
Smoke Density (ASTM E662)	Flaming 103, Non-flaming 109
Slip Resistance (ASTM C-1028)	Dry .7048, Wet .7293
Abrasion Resistance (ASTM D-3884)	700 wear cycles
Cork Binder Resin	formaldehyde-free polyurethane- non-toxic polymer suitable for food contact
Acoustical Isolation & Impact Noise Resistance	FSTC 53 & FIIC 67 on 8 inch concrete slab as per ASTM

This data was compiled in May 2013.

The most recent revision of this document is always available at <http://www.duro-design.com/>